TRANSFER OIL
Pure Fluid Attitude

Crimping details

最近更新： 14/09/2026

084 - 1SB 化学品、液压双功能软管

Transfer Oil reserve the rights to introduce improving modifications whenever necessary.
The listed crimping data have been developed in Transfer Oil R&D laboratories and refer to tests carried out on thermoplastic hoses manufactured by Transfer Oil, and specific Transfer Oil approved ferrules and fittings.
Such values are anyway to be considered advisory and not binding for Transfer Oil because the impossibility to consider technical variability like the swaging machine used, the set of crimping dies used, the speed of the crimping process, the tolerances of each single item involved, etc.
For new applications or for hoses, ferrules and fittings not listed in this file please contact us, and we will be happy to help you in finding the best match.

Part no.	Description	Dash	Inches	DN	ID (mm)	OD (mm)	WP (bar)	WP (psi)	BP (bar)	BP (psi)	Ferrule part n°	Ferrule material	Crimping diameter (mm)	Crimping diameter (inch)	Bore collapse (mm)	Bore collapse (inch)	go/nogo gauge	dies set* (mm)
0841	**3/16 1SB HYDRO-CHEM**	-3	3/16	DN5	5.0	9.7	360	5200	1440	20800	**SAB811**	Stainless Steel (A316L)	**12.1**	**0.476**	**0.3**	**0.0118**	**N/A**	**12**
0841	**3/16 1SB HYDRO-CHEM**	-3	3/16	DN5	5.0	9.7	360	5200	1440	20800	**SAB111**	Carbon Steel	**12.1**	**0.476**	**0.3**	**0.0118**	**N/A**	**12**
0842	**1/4 1SB HYDRO-CHEM**	-4	1/4	DN6	6.5	11.7	310	4500	1240	18000	**SAB821**	Stainless Steel (A316L)	**14.4**	**0.567**	**0.3**	**0.0118**	**N/A**	**14**
0842	**1/4 1SB HYDRO-CHEM**	-4	1/4	DN6	6.5	11.7	310	4500	1240	18000	**SAB121**	Carbon Steel	**14.4**	**0.567**	**0.3**	**0.0118**	**N/A**	**14**
0843	**5/16 1SB HYDRO-CHEM**	-5	5/16	DN8	8.1	13.2	250	3600	1000	14400	**SAB831**	Stainless Steel (A316L)	**16.4**	**0.646**	**0.3**	**0.0118**	**N/A**	**16**
0843	**5/16 1SB HYDRO-CHEM**	-5	5/16	DN8	8.1	13.2	250	3600	1000	14400	**SAB131**	Carbon Steel	**16.4**	**0.646**	**0.3**	**0.0118**	**N/A**	**16**
0844	**3/8 1SB HYDRO-CHEM**	-6	3/8	DN10	9.8	15.5	225	3200	900	12800	**SAB841**	Stainless Steel (A316L)	**18.5**	**0.728**	**0.3**	**0.0118**	**N/A**	**16**
0844	**3/8 1SB HYDRO-CHEM**	-6	3/8	DN10	9.8	15.5	225	3200	900	12800	**SAB141**	Carbon Steel	**18.5**	**0.728**	**0.3**	**0.0118**	**N/A**	**16**
0845	**1/2 1SB HYDRO-CHEM**	-8	1/2	DN12	13.0	18.8	190	2700	760	10800	**SAB851**	Stainless Steel (A316L)	**21.8**	**0.858**	**0.5**	**0.0197**	**N/A**	**19**
0845	**1/2 1SB HYDRO-CHEM**	-8	1/2	DN12	13.0	18.8	190	2700	760	10800	**SAB151**	Carbon Steel	**21.8**	**0.858**	**0.5**	**0.0197**	**N/A**	**19**
0846	**5/8 1SB HYDRO-CHEM**	-10	5/8	DN16	16.3	22.0	140	2000	560	8000	**SAB861**	Stainless Steel (A316L)	**25.4**	**1.000**	**0.5**	**0.0197**	**N/A**	**23**
0846	**5/8 1SB HYDRO-CHEM**	-10	5/8	DN16	16.3	22.0	140	2000	560	8000	**SAB161**	Carbon Steel	**25.4**	**1.000**	**0.5**	**0.0197**	**N/A**	**23**
0847	**3/4 1SB HYDRO-CHEM**	-12	3/4	DN20	19.5	26.0	115	1600	460	6400	**SAB871**	Stainless Steel (A316L)	**29.1**	**1.146**	**0.5**	**0.0197**	**N/A**	**27**
0847	**3/4 1SB HYDRO-CHEM**	-12	3/4	DN20	19.5	26.0	115	1600	460	6400	**SAB171**	Carbon Steel	**29.1**	**1.146**	**0.5**	**0.0197**	**N/A**	**27**
0848	**1 1SB HYDRO-CHEM**	-16	1	DN25	25.8	33.4	95	1300	380	5200	**SAB881**	Stainless Steel (A316L)	**37.4**	**1.472**	**0.5**	**0.0197**	**N/A**	**36**
0848	**1 1SB HYDRO-CHEM**	-16	1	DN25	25.8	33.4	95	1300	380	5200	**SAB181**	Carbon Steel	**37.4**	**1.472**	**0.5**	**0.0197**	**N/A**	**36**

* The dies set indicated are a standard die set for FinnPower FP20 swaging machine, as used in the R&D laboratory of Transfer Oil, used to verify the swaging parameters.