



TRANSFER OIL

Pure Fluid Attitude



039 - JACK HOSE

Thermoplastic hose with steel braid reinforcement for jacking applications up to a static pressure of 700 bar (10000 psi)



FEATURES

Inner Tube

Polyester elastomer

Reinforcement

DN6 – DN 10: two braids of steel wire
DN12: One braid of aramid fiber plus one braid of steel wire

Cover

Polyurethane - black - non pinpricked - laser branding

Applications

High pressure jacking applications - High pressure systems and pumps - Bolt tensioning tools - Re-railing equipment

Features

Robust construction for heavy-duty application and prolonged service life - Double steel braid, or combined reinforcement, offers low volumetric expansion and minimal change in length - High abrasion resistance

Description

High Pressure hose suitable for petroleum or synthetic or water based hydraulic fluids in hydraulic systems for static jacking applications with 2:1 safety factor - Polyurethane cover approved by MSHA (Mine Safety and Health Administration), number IC-305.

Temperature Range

-40 °C to 100 °C (-40 °F to 212 °F): limited to 70 °C (158 °F) for air and water based fluids

Vacuum Rating

-0,93 bar; -700 mm Hg|-13,5 psi; -27,5 inch Hg

Standard Branding

TRANSFER OIL - TO HYDRAULIC - Part No - JACK HOSE - Inch Size - DN Size - WP bar / psi - MSHA IC-305 - MADE IN ITALY - www.transferoil.com - QQ/YY - Batch No

Part no.	DN	Inches	Dash	ID (mm)	OD (mm)	WP (bar)	BP (bar)	ID (inch)	OD (inch)	WP (psi)	BP (psi)	SF	BR (mm)	BR (inch)	Weight (gr/m)	Weight (lb/ft)	Ferrule standard	Ferrule A316L
0392	DN6	1/4	-4	6.4	12.8	700	1400	0.252	0.504	10000	20000	2:1	40	1.57	250	0.168	SAC121	SAC821
0394	DN10	3/8	-6	9.8	16.7	700	1400	0.386	0.657	10000	20000	2:1	65	2.56	380	0.255	SAC141	SAC841
0395	DN12	1/2	-8	13.0	20.5	700	1400	0.512	0.807	10000	20000	2:1	80	3.15	340	0.228	SAC151	SAC851

Multicolor



03Y

*Dimensions and values shown may be changed without prior notice to improve product performances and reliability.
Transfer Oil S.p.A. assumes no liability on mistakes nor errors appearing in this spec sheet.
Document date: 03/07/2026
www.transferoil.com*